

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 2000103689
PUBLICATION DATE : 11-04-00

APPLICATION DATE : 28-09-98
APPLICATION NUMBER : 10274045

APPLICANT : KYOCERA CORP;

INVENTOR : NAKAHARA MASAHIRO;

INT.CL. : C04B 41/87 H01L 21/68 // H01L 21/3065

TITLE : ALUMINA SINTERED COMPACT, ITS PRODUCTION AND PLASMA- RESISTANT MEMBER

ABSTRACT : PROBLEM TO BE SOLVED: To obtain an alumina sintered compact having excellent corrosion resistance to plasma of a halogenated gas and to provide a method for producing the sintered compact.

SOLUTION: A densified alumina sintered compact is embedded in powder of a compound of an element of the group 3a of the periodic table and/or powder of a compound of the formula $3\text{RE}_2\text{O}_3 \cdot 5\text{Al}_2\text{O}_3$ (RE: an element of the group 3a of the periodic table) and heat-treated at $\geq 1,3000^\circ\text{C}$ or the surface of the alumina molding product is coated with a slurry containing the powder of the compound of the element of the group 3a of the periodic table and/or the powder of the compound of the formula $3\text{RE}_2\text{O}_3 \cdot 5\text{Al}_2\text{O}_3$ (RE: the element of the group 3a of the periodic table) and burned at $1,400\text{-}1,800^\circ\text{C}$. A crystalline compound layer of a compound oxide of the element of the group 3a of the periodic table and aluminum, such as $3\text{RE}_2\text{O}_3 \cdot 5\text{Al}_2\text{O}_3$ (RE: the element of the group 3a of the periodic table), etc., is formed on the surface of the alumina sintered compact to improve plasma resistance to plasma of a halogenated gas.

COPYRIGHT: (C)2000,JPO